



GLOBAL TPE SEALING SOLUTIONS

GASKET APPROVED BY THE SECTOR LEADERS



www.cntconta.com

TPV (Thermoplastic Vulcanizate) gaskets

All our gaskets are made of TPV

205



- + Electrical resistivity is high
 (→ 1,0x10¹⁴ per ASTM D257)
- + Environmental friendly products; 100% recyclable
- + UV&Ozon resistance is good
- + Compression set stability in high&low temperatures
- + Producible in Co-Ex and Tri-Ex
- + Suitable for ROSH, Pahs, Reach Certification

Conta Flexible Products - TPV EPDM/PP MSA Clip Insulator Volume Resistivity

 \sim

SAMPLE	RESISTIVITY
1	1.06175E+16
2	8.36320E+15
3	8.33602E+15
4	7.56361E+15
5	8.98076E+15
Mean	8.77222E+15
	(Resistivity → 1,0 x 10¹₄ ASTM D257) approved by First Solar

